



CONDAT SILK SHEET *



WEIGHT	90	100	110	115	130	135	150	170	200	225	250	275	300	350	380
THICKNESS	81	91	101	105	117	123	138	160	188	216	245	281	309	371	414
BULK	0.90	0.91	0.92	0.91	0.90	0.91	0.92	0.94	0.94	0.96	0.98	1.02	1.03	1.06	1.09
WHITENESS	121	121	121	121	121	121	121	121	121	121	121	121	121	121	121
OPACITY	92.5	93.5	95.0	95.5	96.0	96.5	98	98.5	-	-	-	-	-	-	-
PAPER GLOSS	35	35	35	35	35	35	35	35	35	35	35	35	35	35	35
SMOOTHNESS	230	220	180	220	240	220	200	170	270	270	270	250	250	230	200
REL. HUMIDITY 23°C	50%	50%	50%	50%	50%	50%	50%	50%	50%	50%	50%	50%	50%	50%	50%

Property	Standard	Units	Tolerance
Weight	ISO 536	g/m ²	+ / - 4%
Bulk	ISO 534	cm ³ /g	-
Thickness	ISO 534	microns	+ / - 7%
Whiteness CIE D65	ISO 11475	Index	+ / - 3 pts
Opacity	ISO 2471	%	+ / - 2 pts
Paper Gloss	TAPPI T-480	%	+10 / - 5 pts
Smoothness	ISO 5627	sec	+ / - 50%
Relative Humidity	TAPPI T-502	%	+ / - 10 pts



* Those specifications are subject to change without prior notice