



海南金海浆纸业有限公司
HAINAN JINHAI PULP & PAPER CO., LTD.

海南省洋浦经济开发区D12区 邮编:578101
D12,YANGPU ECONOMIC DEVELOPMENT ZONE,HAINAN,CHINA P.C:578101

技术指标 Technical Data (Export Grade)

Category: HI-KOTE C2S Art Paper Gloss Grade(GAH)

FQD-QC1-131204

Item	Unit	Measurement	Technical Data (A)												
			170 GSM	180 GSM	190 GSM	200 GSM	210 GSM	216 GSM	230 GSM	240 GSM	250 GSM	260 GSM	270 GSM	300 GSM	
Basis Weight	g/m2	ISO536	170±6	180±6	190±7	200±8	210±8	216±9	230±9	240±9	250±9	260±9	270±10	300±10	
Thickness	um	ISO534	146±5	154±5	164±5	173±5	183±6	187±6	201±6	216±7	225±7	234±7	244±7	270±8	
	pt		5.74± 0.20	6.06± 0.20	6.46± 0.20	6.81± 0.20	7.20± 0.20	7.36± 0.24	7.91± 0.24	8.50± 0.28	8.86± 0.28	9.21± 0.28	9.61± 0.28	10.63± 0.31	
Opacity	%	ISO2471	98.5±1.5												
Brightness	%	ISO2470	88.5±1.5												
Gloss	%	T480	70±5									65±5			
Roughness	um	ISO8791/4	≤1.4											≤1.6	

Category: HI-KOTE C2S Art Paper Matt Grade(GMH)

Item	Unit	Measurement	Technical Data (A)											
			170 GSM	180 GSM	190 GSM	200 GSM	210 GSM	216 GSM	230 GSM	240 GSM	250 GSM	260 GSM	270 GSM	300 GSM
Basis Weight	g/m2	ISO536	170±6	180±6	190±6	200±8	210±8	216±9	230±9	240±9	250±9	260±9	270±10	300±10
Thickness	um	ISO534	168±6	178±6	188±6	200±6	210±6	216±6	230±7	240±7	250±7	260±8	270±8	285±8
	pt		6.61± 0.24	7.01± 0.24	7.40± 0.24	7.87± 0.24	8.27± 0.24	8.50± 0.24	9.06± 0.28	9.45± 0.28	9.84± 0.28	10.24± 0.31	10.63± 0.31	11.22± 0.31
Opacity	%	ISO2471	98.5±1.5											
Brightness	%	ISO2470	88.5±1.5											
Gloss	%	T480	30±5											
Roughness	um	ISO8791/4	≤2.5											



Fine Paper Quality Control Division
HAINAN JINHAI PULP&PAPER CO., LTD.

2013/12/04