



**MOUGEOT
COPY**



Carbonless Paper

Selbstdurchschreibepapier Rolle
Carbonless paper in reels

Merkmal Property	Prüfnorm Standard	Einheit Unit	Wert Value					Toleranz Tolerance
			CB 50*	CB 55	CFB 53	CF 50*	CF 55	
Flächengewicht Basis weight	ISO 536	g/m ² gsm	50	55	53	50	55	± 5 %
Dicke Caliper	ISO 534	µm	70	74	70	60	70	± 5
Glätte Bekk (OS) Smoothness Bekk (TS)	ISO 5627	s	35	35	45	50	50	± 20
Weiße R457 Brightness R457	ISO 2470	%	98	98	92	93	93	± 3
Reißlänge längs Breaking length md	ISO 1924-1	m	6.500					± 1.500
Feuchte absolut Absolute humidity		%	5,8					± 0,3

Änderungen vorbehalten / subject to change without notice / sujeto a cambio sin previo aviso

* CB 50 / CF 50 nur auf Anfrage
CB 50 / CF 50 only on request



Koehler
PAPER GROUP

Papierfabrik August Koehler SE

Hauptstraße 2 · 77704 Oberkirch, Germany · Phone +49 7802 81-0 · Fax +49 7802 81-4330 · www.koehlerpaper.com