



pindo deli
paper products


FO/001/1
Rev : 1


UNCONTROLLED COPY


SPECIFICATION		DOC. NO.	SP/6/204/1041
		REVISION	1
		DATE OF ISSUE	22/04/2009
		PAGE	1 OF 1
TITLE : CARBONLESS PAPER CB 46, 50, 55, 60, 75, 80 & 90 GSM (R) IMPRESSION 2000			

NO	PARAMETER	UNIT	CB 46	CB 50	CB 55	CB 60	CB 75	CB 80	CB 90	TEST METHOD
1	Basis Weight	g/m ²	46 ± 1	47 - 51	52 - 56	60 ± 2	73 - 77	80 ± 2	90 ± 3	ISO 536: 1995
2	Thickness	micron	69 ± 3	72 ± 3	77 ± 3	84 ± 3	103 ± 3	108 ± 3	120 ± 4	ISO 534: 2005
3	Bendsen Roughness	ml/min TS BS	<u>Max. 180</u> Max. 500	Max. 180 Max. 500	Max. 180 Max. 500	Max. 180 Max. 500	Max. 180 Max. 500	Max. 190 Max. 550	Max. 200 Max. 550	ISO 8791-2; 1990
4	Copy Intensity	%	<u>Min. 29</u>	<u>Min. 29</u>	<u>Min. 29</u>	<u>Min. 29</u>	<u>Min. 29</u>	<u>Min. 29</u>	<u>Min. 29</u>	-

Note : TS = Top Side BS = Bottom Side
Printer Type for Intensity : EPSON LQ - 2180 Standard Resolution 180 x 180 dpi

Prepared By: 
Sec. Head of QC
Date: 21/4/2009

Approved By: 
Head of QC (Laboratory)
Date: 21/4/2009

Approved By: 
Production Manager
Date: 22/4/2009


Head of Tech. Division
Date: 22/4/2009